



PUNCTURED & DRIPABLE

PRODUCT DESCRIPTION:

SPECIAL PLASTIC FOR RELIEF APPLICATIONS FOR DIFFERENT TECHNIQUES AS GOTELE, PUNCTURED, STRIPED AND RUSH MATTING, ETC. FOR APPLICATIONS IN RELIEF WITH BIG DROPS, APPLY DIRECTLY W/O DILUTION.

TECHNICAL CHARACTERISTICS:

COLOUR:	WHITE
FINISHING:	MATTE
DILUTE:	WATER
DENSITY:	1.7 gr/cc APPROX
VISCOSITY:	20.000-30.000 C.P.S.
TACT DRYING:	30 MIN APPROX
PERFORMANCE:	4-5 m ² /Kg-Lt DEPENDING ON SURFACE CONDITIONS
RE-PAINTING:	AFTER 4-5 HOURS
VISCOSITY:	60.000 CENTIPOISE 5, BROOKFIELD, Sp-6,10 r.p.m. 23°C
WASHABILITY:	EXCELLENT ACCORDING TO DIN 53778 SPECIFICATION
WAREHOUSING:	EXCELLENT IN ITS ORIGINAL CLOSED PACKAGE AT NORMAL HUMIDITY & TEMPERATURE
PACKAGING:	3, 9 & 14 LTRS IML PLASTIC / LITHOGRAPHED METALLIC TIN

PROPERTIES:

HIGH WHITENESS COVERING UP PAINT. HAS ENOUGH RESSISTANCE TO THE HUMID RUB TO BE APPLIED IN INTERNAL ENVIRONMENTS. EASY APPLICATION. BREATHABLE.

USE METHOD:

CAN BE APPLIED WITH BRUSH, ROLLER OR AIRLESS GUN ON CLEAN AND DRY SURFACES W/O RUST, DUST, GREASE, HUMIDITY, SALTPETRE, ETC. OLD PAINTS MUST BE REMOVED AND CLEAN FROM THE SURFACE TO ENSURE THE RIGHT ADHESIVENESS. THE SURFACES TO BE PAINTED MUST BE FIRST PREPARED WITH ADORCRIL COLOURLESS ACRYLIC VARNISH OR WITH THE SAME PUNCTURED AND DRIPABLE PLASTIC DILUTED AT 10%. DO OT APPLY AT TEMPERATURES BELOW 5°C OR OVER 35°C

REV. 02.06.11

With this technical card, based on our experience and research, we only pretend to inform and advise you according to our knowledge and good faith, In any case we can not be responsables for the use of this product under circumstances and conditions of its application, due to be out of our own control.

Crta. Nacional 301- km.215.700
02630 La Roda (Albacete) Spain
Ph.: +34 967 44 38 38- Fax: +34 967 44 38 14
info@pinturasadoral.com
www.pinturasadoral.com